



PRODUCT DATA

PRODUCT DATA

PRODUCT DATA

PRODUCT DATA

DESCRIPTION

We did not produce a Product sheet on this product as E-Bond 575 is a custom formula of Resin and Hardener only to be combined with a Component "C" aggregate to be supplied by others.

TYPICAL DATA

All components conditioned cured and tested at 75°F (23°C) unless specified otherwise.

Color:	Part A Resin Part B Hardener Admix	Opaque liquid. Straw Straw
Mixing Ratio:		2A to 1 B by Volume 100 to 42 by Weight
Viscosity:	ASTM-D-2393 #2 @ 20 rpm Part A cps Part B cps Admix cps	700 1100 900
Pot-Life:	142 gms @ 75°F (A+B)	135 minutes
Working Time:	@ 75°F (A+B+C)	2-2 ½ hours
Shore D Durometer:		75 70/10
Tensile Properties:	ASTM D 638 psi min	1500

Suggested Unit Packaging: A one-gallon unit t packaged in a three-gallon bucket consisting of three components.

Component "A" Epoxy Resin: 3.312 lbs (46.1 fluid ounces 1,363 ml) in a one half-gallon plastic container.

Component "B" Epoxy Hardener: 1.392 lbs (22.8 ounces, 647 ml) in an F-Style Quart Container with a Child Proof Cap and aluminum foil seal.

Component "C" Aggregate: 9-10.22 lbs. in a plastic bag.

The plastic bag will be placed on the bottom of a 3-gallon container, ½ gallon container of epoxy resin and the quart container of hardener will be placed and the container sealed .Will produce 3.7 Liters and/or one-gallon (totals A & B & C Compounds).

Shelf Life: 2 years in original unopened container.

Storage: Store Dry at 40°F (4.4°C)-95°F(35°C) .Condition to 65°F (18°C)-75°F(24°C) before using. Protect from inclement weather and freezing.



CAUTION

- Consult material safety data sheet for more information.
- Do not apply when substrate surface temperature is 120°F (49°C) or higher, high daily temperature cycles may cause out gassing and resist penetration of Sealer.
- Do not apply over wet, shimmering surface, or concrete subject to hydrostatic pressure.
- For applications on exterior on-grade substrates, consult Technical Service.
- Use only bagged oven-dry aggregate of required size and shape.

For professional use only; not for sale to or use by the general public. E-Bond's epoxies contain alkaline amines. Strong sensitizer; MAY CAUSE SKIN SENSITIZATION or allergic response ranging from a mild wheezing to a severe asthmatic type attack. Avoid contact with skin or eyes. IN CASE OF CONTACT immediately wash skin with soap and water. Flush eyes with water and obtain medical attention. Wear protective clothing, goggles, and barrier cream on all exposed skin

LIMITED WARRANTY NOTICE: Every reasonable effort is made to apply E-BOND exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, E-BOND MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and E-BOND shall have no other liability with respect thereto. E-Bond excludes any warranty for discoloration or change in visual appearance of the product due to accumulation of or streaking of dirt or other airborne materials deposited on the surface from the atmosphere. E-BOND does not warrant the colorfastness of any product. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the E-BOND Technical Manager.

This information and all further technical advice are based on E-BOND's present knowledge and experience. However, E-BOND assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, E-Bond disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. E-BOND SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. E-BOND reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out by qualified experts. It is the sole responsibility of the customer to carry out and arrange for such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

E-BOND EPOXIES, INC.
501 N.E. 33RD ST
P.O. BOX 23069
FT. LAUDERDALE, FL 33307
TOLL FREE : (877) 265-0011
PHONE: (954) 566-6555
FAX: (954) 566-6663
E-Mail: info@ebondepoxies.com
www.ebondepoxies.com